

### Silver Travertine Physical Characteristics

| Test Item                | Test Criterion     | Test Result |
|--------------------------|--------------------|-------------|
| Wet Compressive Strength | Kg/cm <sup>2</sup> | 204.6       |
| Dry Compressive Strength | Kg/cm <sup>2</sup> | 258.3       |
| Density                  | Kg/m <sup>3</sup>  | 2650        |
| Water Absorption         | %                  | 2.65        |

### Silver Travertine Chemical Characteristics

|                                |          |
|--------------------------------|----------|
| CaO                            | 54.67%   |
| Fe <sub>2</sub> O <sub>3</sub> | 0.344 %  |
| MgO                            | --       |
| Al <sub>2</sub> O <sub>3</sub> | 0.0056 % |
| SiO <sub>2</sub>               | 0.474 %  |